

HARDNESS COMPARISON CHART

RW/C Brinell

64	722
62	688
60	654
58	615
56	577
54	543
52	512
50	481
48	455
47	443
46	432
45	421
44	409
43	400
42	390
41	381
40	371
39	362
38	353
37	344
36	336
35	327
34	319
33	311
32	301
31	294
30	286
29	279
28	271
27	264
26	258
25	253
24	247
23	243